

ESA80 Eco-sol Silver Adhesive 80

PRODUCT SPECIFICATION

1. General Properties

Property	Unit	Spec	Value	Test Method
Appearance	-	Satin	Pass	ASTM E284
Base Thickness	μm	50 ± 5	50	ASTM D645
Base Weight	g/m ²	70 ± 5	71	ASTM D646
Total Thickness	μm	150 ± 5	148	ASTM D645
Total Weight	g/m ²	190 ± 5	189	ASTM D646
Gloss	%	60°: 62 ± 3	60°: 62	ASTM D2457
L. a. b.	-	L : 99.0 ≤ a : -0.1 ± 0.2 b : 0.3 ± 0.2	L : 97.66 a : -0.08 b : 0.26	ANSI T (D65/2°/Abs/No)
Whiteness	-	94 ± 3	93.12	ASTM E313
Peel Strength	gf/25mm	1,000 ± 100	950	ASTM D903

※ Peel Strength : 180° Peel이며, Substrate(피착재)는 Glass.



This document is based upon JOHNS MEDIA quality system & procedures.
JOHNS MEDIA supply a copy to customer after investigating and approval.