



ARLON

## ► Series 3210 Overlaminates

### Premium Cast Overlaminates Pressure-Sensitive Film

Series 3210 overlaminates are constructed of a 1.3-mil (35 microns) gloss cast vinyl film with clear, permanent pressure-sensitive adhesive. Designed to protect printed images and prolong the life of the printed images. Series 3210 provides the same protection as our standard overlaminates while having excellent conformability during installation with a lighter weight film. The gloss finish provides an extra pop to printed graphics. Series 3210 is rated for outdoor durability up to 7 years. This product is not designed to be used as an optically clear window film.

### APPLICATIONS & FEATURES

- Protective overlaminates for SLX™ Cast Wrap, DPF 6100XLP, DPF 6000XRP, DPF 6000RP White, DPF 6000RP Clear, DPF 6500, DPF 6700, IllumiNITE Wrap™, DPF 2400, DPF 4600LX, DPF 4500GT/MT, DPF 8000™ Ultra Tack, DPF 8200 High Tack, DPF 9000, DPF 4000, DPF 4300.
- Fleet graphics, vehicle applications, long-term signage, kiosks and POP displays.
- UV inhibitors to protect and extend the life of your printed graphic.
- Arlon overlaminates film is designed to be laminated cold without any heat.

### PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
<b>SURFACE FINISH</b>	Gloss Meter 60° Reflection	80 to 90 Gloss Units	
<b>THICKNESS</b>	Micrometer, Federal Bench Type	1.3 mil (35 microns)	
<b>TENSILE STRENGTH</b>	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 6.5 lb/in	≥ 1.2 kg/cm
<b>ELONGATION</b>	Instron Tensile Tester as above	≥ 200%	
<b>SHELF LIFE (IN BOX)</b>	Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	2 years from factory shipment	
<b>APPLICATION TEMPERATURE RANGE</b>	On clean, dry substrate		
	Flat:	40°F to 100°F	4.4°C to 38°C
	Corrugated with rivets & channels:	60°F to 100°F	15°C to 38°C
<b>SERVICE TEMPERATURE RANGE</b>	On clean, dry substrate	-40°F to 175°F	-40°C to 79°C
<b>DIMENSIONAL STABILITY</b>	Shrinkage After 158°F (70°C), 48 hours	< 10-mil	0.25 mm
<b>PEEL ADHESION</b>	PSTC-1, 15 min, 70°F (21°C)	3.0 lbs/in	0.535 kg/cm
<b>LINER RELEASE</b>	TLMI Release at 90°, 300 in/min (760 cm/min)	37 g/2in	7.28 g/cm

Standard Terms & Conditions Apply

## TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

*March 2018*