

Self-adhesive Digital Imaging Media for wide-format solvent-based & UV inkjet Printing

WW 300

4 year monomeric calendered vinyl

Technical Data Sheet

PRODUCT DESCRIPTION

FACE MATERIAL : 100 μ white matt soft calendered PVC film.
ADHESIVE : High Tack Permanent opaque acrylic.
LINER : Coated Kraft liner 140 gsm backprinted MACTac/IMAGin

TYPICAL USES

Designed for medium term indoor or outdoor on **difficult substrates**.
The very high tack & adhesion properties of this product will make it adhere to a wide variety of substrates including **most types of flat walls**, interior or exterior and **even on latex painted walls**, often regarded as the most difficult paints.
Industrial applications: road/forest/builders' machines, waste containers, trivison panels.

PRINTING

Designed for solvent based/eco-solvent & UV inkjet and Latex inkjet printing on wide-format printing equipment.

To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used.
Profiles can be obtained from our Subsidiaries, Distributors or can be downloaded from www.mactac-europe.com.
Printer & Heater settings and ICC profiles are also downloadable from some of the OEM's web sites.

PHYSICAL PROPERTIES OF THE UNPRINTED FILM

	<u>Average values</u>	<u>Test method</u>
<u>Adhesive Data, 23°C</u> Quick Tack on glass Peel 24 hours on glass	24 \pm 5 N/25 mm 26 \pm 6 N/25 mm	FTM 9 FTM 1
<u>Dimensional stability</u> shrinkage : 48 hours at 70°C (applied on aluminium)	max 1.0 mm	FTM 14
<u>Temperature ranges</u> Minimum application temperature : Service temperature range :	+ 10°C - 20°C to + 70°C	
<u>Flammability</u>	Self-extinguishing	Mactac Internal test method
<u>Solvent resistance</u>	No effect	Applied to stainless steel. Exposed to: oils, greases, aliphatic solvents, alcohols, mild acids, mild alkalis.
<u>Petrol resistance</u>	If extended contact, edge-lifting will occur.	Repeated (each 10 min) petrol spraying.

SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

DURABILITY

The outdoor durability of the unprinted film is 4 years (Middle European Exposure conditions, vertical exposure).

Overlamination of the inkjet printed material delays eventual colour fading that may occur upon time.

This colour fading is dependent from the quality of the inkjet inks, the orientation of the printed material, the angle of display and the exact location of exposure on the Globe.

RECOMMENDATIONS

Always test the combination of JT 5000 products, inks and laminating films prior to commercial use.

> Printing conditions

A conditioned pressroom, ± 23°C and 50 % R.H.

> Laminating conditions

Please ensure the print is perfectly dry. The printed material should be left to dry for at least 48 hours prior to lamination or transport.

If the printed graphics is likely to be exposed to corrosive liquids, smoke, fumes, highly polluted areas or if there is a likelihood of scratching or friction or to ensure longer durability, it is strongly recommended to laminate the prints with pressure-sensitive protective films IMAGin LF 3899 (glossy), LF 3898 (matt), LF3894 (satin), Permafun Crystal Gloss or any laminate from the PG7200 series.

MACtac denies responsibility for product failure if non-MACtac laminating films are used for the application.

> Transportation conditions

To allow easy transportation, IMAGin JT series can be rolled up, with the image on the outside, with a minimum diameter of 15 cm (for example on a 6 inches core).

When the image is not protected with a laminating film, make sure that the print is perfectly dry before rolling it over.

To avoid exposing the print to any liquid aggressions, prints should be protected by a plastic bag. During the transport or storage of the prints, avoid exposing them to extreme temperature and humidity variations.

GENERAL REMARK : factors affecting adhesion

To ensure application suitability - always test the proposed construction under actual application and end-use conditions before going into full production.

The following factors will adversely affect adhesion of a pressure-sensitive adhesive:

- * Dusty, dirty, oily or oxidized surfaces
- * Mould release agents on blow-moulded plastic surfaces
- * Low surface energy substrates, such as: polyethylene, polypropylene...
- * Application below the minimum application temperature or use outside of the recommended service temperature ranges.

IMPORTANT NOTICE

All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects.

Published information concerning MACtac products is based upon research which the Company believes to be reliable although such information does not constitute a warranty.

Because of the variety of uses of MACtac products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages.

All specifications are subject to change without prior notice.

